



2479, 1322, 0767

Swisspearl Group AG
Eternitstrasse 3, Niederurnen, CH-8867
Switzerland

17

DoP_PGF

EN12467:2012+A1:2016

*Fibre-cement flat sheets with plane and structured
surface for internal and external applications and
cladding*

NT

Swisspearl®Largo Panels

**Net sizes (maximal values):
3050x1250x12 mm**

Mechanical resistance:	A4
Dimensional stability:	
- unedged Panels:	Level II
- edged Panels:	Level I
Reaction to fire:	A2-s1, d0
Water impermeability:	No water drops
Release of dangerous substances:	No performance declared (NPD)
Resistance against:	
- Freeze-thaw:	$R_L \geq 0.75$
- Warm water:	$R_L \geq 0.75$
- Wet-dry:	$R_L \geq 0.75$
- Heat-rain:	Fulfilled